CORROSION RESISTANCE CHART

Warning: Corrosion rates may vary widely with factors such as concentration, temperature, abrasion and impurities of product. Serious injury may occur with contact of incompatible liquids with solids.

Compatibility Ratings

A = Excellent B = Good C = Fair to poor D = Poor Recommedation X = Not recommended - = No data available

Temperature Ratings:

1 = OK to 80° F 3 = OK to 95° F
2 = OK to 125° F 4 = OK to 205° F
All others listed at ambient temperature

	Epoxy		Plastics															Elastomers											Metals										Non-Metals		
CHEMICAL	Vinyl Ester VR-1	Epoxy EY-1	ABS Plastic	Acetal (Delrin)	CPVC	Epoxy	Hytrel®	HDPE	LDPE	Nonyl®	Nylon	Polycarbonate	Polypropylene	PPS (Ryton)	PTFE (Teflon)	PVC	PVDF (Kynar®)	Buna N (Nitrile)	EPDM	Hypalon®	PCTFE	Natural rubber	Neoprene	Santoprene	Silicone	Tygon® (R-3603)	Viton®	304 stainless steel	316 stainless steel	Aluminum	Brass	Bronze	Carpenter 20	Cast iron	Copper	Hastelloy-C®	Titanium	Carbon graphite	Ceramic Al_2O_3	Ceramic magnet
Iodine (in alcohol)	-	-	-	D	-	-	-	B	B	-	C	-	-	-	-	A	A	-	A	-	-	-	-	-	-	-	-	-	-	B	-	B	-	-	-	B	B	-	-	-
Iodine, Crystals	A^2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	C	-	-	-	C	-	-	B	D	-	-	-
Iodoform	-	-	-	-	-	-	-	-	-	-	-	-	-	-	C	A	C	D	A	-	A	B	A	B	-	C	-	A	A	A	-	-	A	A	B	A	B	-	-	-
Iron and steel Cleaning Bath	A^2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	D	-	-	-	D	-	-	A	D	-	-	-
Iron Plating Solution	A^2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	C	-	-	-	B	-	-	B	A	-	-	-
Isoamyl Acetate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	X	B	-	A	-	X	-	-	-	X	-	A	A	-	-	-	A	-	A	-	-	-	-
Isoamyl Butyrate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	X	-	-	A	-	-	-	-	-	X	-	A	A	-	-	-	A	-	A	-	-	-	-
Isoamyl Chloride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	X	X	-	A	-	X	-	-	-	A	-	-	X	-	-	-	-	-	-	-	-	-	-
Isobutyl Acetate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	X	C	-	A	-	X	-	-	-	X	-	A	A	-	-	-	A	-	A	-	-	-	-
Isobutyl Amine	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	X	-	-	A	-	-	-	-	-	X	-	-	-	-	-	-	-	-	-	-	-	-	-
Isobutyl Chloride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	X	-	-	A	-	-	-	-	-	B	-	B	X	-	-	-	B	-	B	-	-	-	-
Isobutyric Acid	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	X	A	-	A	-	B	-	-	-	-	-	-	A	-	-	-	-	-	A	-	-	-	-
Isodecanol	A^2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	A	-	-	A	-	-	-	-
Isododecane	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	B	X	-	A	-	A	-	-	-	A	-	B	B	-	-	-	B	-	-	-	-	-	-
Isooctane	-	-	-	-	-	A^2	A	B	B	D	A^1	B^1	A^2	A	A	A^1	A^2	A^2	D	-	A^1	A^1	B^1	D	D	D	A^1	A^1	A^1	A^1	A	A^1	-	-	-	-	-	A^2	-	-
Isooctane (Trimethylpentane)	-	-	-	-	-	-	A	-	-	-	-	-	A	A	A	-	A	A	X	-	A	-	B	C	-	-	A	-	A	A	-	-	-	A	-	A	-	-	-	-
Isopentane	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	A	-	-	A	-	-	-	-	-	A	-	-	-	-	-	-	-	-	A	-	-	-	-
Isophorone	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	X	C	-	A	-	X	B	-	-	X	-	A	A	-	-	-	A	-	-	-	-	-	-
Isopropyl Ether	-	-	-	D	-	D	-	D	B	-	A^1	D	B	-	A^1	B	A/70%	B	D	C	A	A	D	B	D	D	C	A	A	A	A	A	A	-	B	A	-	A	-	-
Isopropyl Acetate	-	-	-	D	-	A	C	B	B^1	-	B^1	D	B^1	-	A	D	D	D	B	D	A	D	D	B	D	D	D	C	A	D	-	A^1	B	A	-	B	-	A	-	-
Isopropyl Alcohol	A^2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	B	-	-	-	A	-	-	B	A	-	-	-
Isopropyl Amine	A_2	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	X	-	-	A	-	-	-	-	-	X	-	A	-	-	-	-	A	-	B	B	-	-	-
Isopropyl Chloride	-	-	-	-	-	-	-	-	-	-	-	-	X	-	A	-	-	X	X	-	A	-	X	C	-	-	B	-	A	X	-	-	-	A	-	A	-	-	-	-
Isopropyl Myristate	A^4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	B	-	-	-	A	-	-	-	-	-	-	-
Isopropyl Palmitate	A^4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	B	-	-	-	A	-	-	-	-	-	-	-
Isotane	-	-	-	-	-	A	-	-	-	-	D	-	D	-	-	A	A	A	-	-	-	-	D	-	-	-	A	-	-	D	-	-	-	-	-	-	-	-	-	-
Jet Fuel (JP1 to JP 6) (ASTM-A, A1 & B)	-	-	-	A	-	-	X	-	-	-	-	-	X	A	A	-	A	A	X	-	A	-	C	X	-	-	A	-	A	A	-	-	-	A	-	A	-	-	-	-
Jet Fuel (JP3, JP4, JP5, Jp8)	A^2	A^4	-	A^1	-	A	-	D	D	D	C	A^1	A^1	A	A	C	B	A	D	D	A	D	D	D	D	D	D	A	A	A	-	A	A	A	A	A	A	A	-	-
Kerosene	A^2	A^4	D	A^2	-	A	C	B	C^1	D	A	D	B	A	A	A^2	A	A	D	D	A	D	A	D	D	D	A	A	A	A	A	A	A	B	A	A	B	A	B
Ketones	-	-	A	D	-	C	-	D	C^1	D	A^2	D	C	A	A	D	C^1	D	A	-	B^1	A	D	D	-	D	D	A	A	B	-	A	A	-	A	A	A	A	A	-
Lacquer, Thinners	-	-	A	D	-	A	D	D	A	D	A^1	B	D	-	A	D	-	D	D	D	-	D	D	-	D	D	D	A^1	A	A	A	A	A	C	A	A	C	A	-	-
Lacquers	-	-	A	B	-	A	X	D	A	D	A^1	D	D	-	A	D	D	D	D	D	A	D	D	C	D	A	D	A^1	A	A	-	A	A	B	A	A	-	A	-	-
Lactic Acid	A^4	-	D	B	A^1	B^1	D	A	A^1	A	B	B	A	A	A	B^1	A	A	A	A	A^1	A	A	A	A	A	A	B^1	A/70°	A	D	B^2	C	D	B	A	A	A	A	-
Lactol (Aliphatic Naptha Solvent)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	C	-	-	A	-	X	-	-	-	A	-	A	A	-	-	-	A	-	A	-	-	-	-
Lard	-	-	-	A	-	B	-	A	A	A	A^1	A^1	B^1	-	A	A^1	A	A	D	B	-	D^1	D	A	B	D	A	A	A	A	-	A	A	A	-	A	A	A	-	-
Latex	A^2	-	B	B	-	A	A	-	-	-	A^1	-	A^2	-	A	-	A	A	A	-	A	-	A	A	A	A	A	A^2	A^2	A	-	-	A	-	-	A	-	-	-	-
Lauric Acid	-	A^4	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	-	-
Lauryl Alcohol	A^3	A^2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	-	-
Lauryl Chloride	A^3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	B	-	-	-	-	-	-	-
Lead Acetate	A^4	A^4	B	B	A^2	A	-	A	A^2	A^1	A	-	A^1	A	A	B	A	B	A	D	A	A	A	A	A	B	D	B	B^1	D	-	B^1	A	A	-	B^1	A^1	A	A	-

Warning: Halogenated solvents such as 1,1,1, Trichloroethane and Methylene Chloride should not be used in Aluminum equipment. A violent explosion could occur with halogenated hydrocarbons such as Carbon Tetrachloride, Chloriform, Dichlorethylene, Methyl Chloride, Methylene Chloride, and Trichlorethylene.

Data shown is based on information that has not been independently verified. We do not guarantee its accuracy or imply or state the accuracy of these charts. Data is limited to the concentrations and temperature specified. Assume ambient temperatures where temperature restrictions are not indicated.